

96% Alumina Ceramic Material Properties-SU0627

Properties	Unit	Value
Composition	%	AL ₂ O ₃ ≥96 SiO ₂ ≤1.5 Fe ₂ O ₃ ≤0.05 Na ₂ O ≤0.1 MgO ≤1.5
Volume Density	g/cm ³	≥3.75
Bending Strength	MPa	> 250
Linear Expansion Coefficient (20-500°C)	x10 ⁻⁶	6.5~7.5
Thermal Conductivity (20°C)	W/(m·k)	≈25
Specific Resistance	100°C Ω.cm	≥10 ¹³
Hardness	HV5	≥1050

Remark: The value is just for review, different using conditions will have a little difference.

Xiamen Innovacera Advanced Materials Co.,Ltd

 Block A, 6/F, No.588 Jiahe Road, Torch High-tech Industrial District, Xiamen, China 361006.

 0086 592 558 9730

 0086 592 558 9733

 sales@innovacera.com

 www.innovacera.com